

Description

Method of Manufacturing Spindle Motor

BACKGROUND OF INVENTION

FIELD OF THE INVENTION

[0001] The present invention relates to a method of manufacturing a spindle motor in which an oil repellent film is formed by applying an oil repellent solution to a predetermined area of a rotating member and/or a stationary member constituting the spindle motor.

DESCRIPTION OF THE PRIOR ART

[0002] In recent years, in the spindle motor which is used for driving a recording medium such as a hard disc or the like, a hydrodynamic bearing utilizing a lubricating oil begins to be employed. The hydrodynamic bearing is provided, for example, with a hollow cylindrical sleeve having a bearing hole, a shaft fitted and inserted to the bearing hole at a micro gap in radial direction, and a lubricating oil filling the micro gap, and the sleeve and the shaft are supported so as to relatively rotate freely.

[0003] In this hydrodynamic bearing, there is a risk that the lubricating oil leaks out to an external portion of the hydrodynamic bearing along surfaces of the shaft and the sleeve. Accordingly, in order to prevent the lubricating oil from leaking out to the external portion of the hydrodynamic bearing, an oil repellent solution is applied to the surface of the shaft and/or the sleeve positioned near the hydrodynamic bearing, and an oil repellent film is formed thereon.

[0004] As an apparatus for coating the oil repellent solution, for example, the following oil repellent coating apparatus is disclosed in Japanese Patent Application Laid-open Publication No. 2001-232289. In other words, a deformed inner diameter portion in which an inner diameter is non-linearly changed in axial direction is formed in an inner peripheral portion of an annular bearing member. The oil repellent coating apparatus is provided with a coating head having a columnar projection portion including an opening portion in radial direction and fitted to the deformed inner diameter portion of the bearing member at a predetermined gap, and a seat portion with which a lower end surface of the bearing member is brought into contact, and automatically and evenly applies the oil repellent

solution to the deformed inner diameter portion of the bearing member.

[0005] In this case, a recording medium driving apparatus using the spindle motor or the other apparatus is promoted in a downsizing and a thin structure, and the spindle motor used in the apparatus is also promoted in a downsizing and a thin structure. Accordingly, an area in the spindle motor in which the oil repellent film should be formed for preventing the lubricating oil from leaking out is going to be further narrowed.

[0006] In particular, since the oil repellent solution is applied to a part of the predetermined area on the surface of the shaft and/or the sleeve, and is thereafter going to spread along the surface, the oil repellent solution runs over the predetermined area and the oil repellent film tends to be formed.

[0007] In the oil repellent coating apparatus described in Japanese Patent Application Laid-open Publication No. 2001-232289 mentioned above, it is possible to automatically apply the oil repellent solution to the deformed inner diameter portion in which the inner diameter is non-linearly changed. However, in the deformed inner diameter portion, it is impossible to control the area in which

the oil repellent solution spreads so as to accurately form the oil repellent film in the predetermined area.

SUMMARY OF INVENTION

[0008] An object of the present invention is to accurately form an oil repellent film on a predetermined area of a member constituting a spindle motor by controlling the area in which an oil repellent solution spreads.

[0009] Further, another object of the present invention is to provide a spindle motor manufacturing method which can manufacture the spindle motor in which the oil repellent film is accurately formed.

[0010] A spindle motor in accordance with one aspect of the present invention has a stationary member, a rotating member and a hydrodynamic bearing, the hydrodynamic bearing having a gap formed between said stationary member and said rotating member and having a lubricating oil retained in the gap for supporting said rotating member with respect to said stationary member in a rotatable manner. Further, the one aspect of the present invention relates to a spindle motor manufacturing method of forming an oil repellent film for preventing the lubricating oil from flowing out, in a predetermined area adjacent to the hydrodynamic bearing, the predetermined area

being located on at least one of the stationary member and the rotating member.

[0011] The spindle motor manufacturing method mentioned above comprises a step of supplying an oil repellent solution by a supplying portion onto a part of the predetermined area for forming the oil repellent film, a step of applying an air current to the part of the predetermined area on which the oil repellent solution is supplied so as to peel off an excess part of the oil repellent solution supplied onto the part of the predetermined area, and a step of making a relative movement of the predetermined area in which the oil repellent film is formed, the relative movement being made with respect to the supplying portion by which the oil repellent solution is supplied.

[0012] In accordance with the method mentioned above, it is possible to control the spread of the oil repellent solution in the predetermined area on which the oil repellent film is formed, and it is possible to remove a supplied excess oil repellent solution.

[0013] In this case, the peeling step can employ a method of sucking and removing the supplied excess oil repellent solution, a method of blowing out and removing the supplied excess oil repellent solution.

[0014] Another manufacturing method of a spindle motor comprises a step of supplying an oil repellent solution by a supplying portion onto a part of the predetermined area for forming the oil repellent film, a step of applying an air current onto the part of the predetermined area on which the oil repellent solution is supplied so as to peel off an excess part of the oil repellent solution supplied to the part of the predetermined area, a step of making a relative movement of the predetermined area in which the oil repellent film is formed, and the relative movement is made with respect to the supplying portion, a step of supplying a solvent for solving the excess part of said oil repellent solution, peeled off in said applying air current step; and a step of removing said oil repellent solution dissolved by the solvent.

[0015] In the case of using a volatile oil repellent solution, the oil repellent solution tends to be solidified for a short time. In accordance with the another method of the present invention, the solvent is added to the peeled oil repellent solution by supplying the solvent in which the oil repellent dissolves. Accordingly, it is possible to prevent the peeled oil repellent solution from being solidified, and it is possible to smoothly recover the peeled oil repellent solution.

BRIEF DESCRIPTION OF DRAWINGS

- [0016] Fig. 1 is a cross sectional view showing a spindle motor in accordance with the present invention;
- [0017] Fig. 2 is a partly enlarged cross sectional view of the spindle motor in Fig. 1;
- [0018] Fig. 3 is a perspective view showing a coating step of an oil repellent solution in accordance with a first embodiment of the present invention;
- [0019] Fig. 4 is a perspective view showing the coating step of the oil repellent solution in accordance with the first embodiment of the present invention;
- [0020] Fig. 5 is a perspective view showing the coating step of the oil repellent solution in accordance with the first embodiment of the present invention;
- [0021] Fig. 6 is a perspective view showing the coating step of the oil repellent solution in accordance with the first embodiment of the present invention;
- [0022] Fig. 7 is a perspective view showing the coating step of the oil repellent solution in accordance with the first embodiment of the present invention;
- [0023] Fig. 8 is a perspective view showing the coating step of the oil repellent solution in accordance with the first embodiment of the present invention;

- [0024] Fig. 9 is a perspective view of a main portion with respect to a suction apparatus and a supply apparatus;
- [0025] Fig. 10 is a cross sectional view showing a coating step of the oil repellent solution in accordance with a second embodiment of the present invention;
- [0026] Fig. 11 is a schematic view showing a cleaning step of a supply nozzle;
- [0027] Fig. 12 is a schematic view showing the cleaning step of the supply nozzle;
- [0028] Fig. 13 is a schematic view showing the cleaning step of the supply nozzle; and
- [0029] Fig. 14 is a schematic view showing the cleaning step of the supply nozzle.

DETAILED DESCRIPTION

- [0030] A description will be given below of a method of manufacturing spindle motor in accordance with respective embodiments of the present invention with reference to Figs. 1 to 14.
- [0031] Fig. 1 shows an example of a spindle motor showing the present invention. Fig. 2 is a partly enlarged cross sectional view of the spindle motor shown in Fig. 1.
- [0032] A spindle motor is provided with a stationary member 52, a rotating member 54 and a hydrodynamic bearing 56.

The rotating member 54 is rotatably supported by the hydrodynamic bearing 56 structured between the rotating member 54 and the stationary member 52. The hydrodynamic bearing 56 is constituted by an outer peripheral surface of an approximately cylindrical shaft 58 of the stationary member 52, an inner peripheral surface of a hollow cylindrical sleeve 60 of the rotating member 54, and a lubricating oil filled between the outer peripheral surface of the shaft 58 and the inner peripheral surface of sleeve 60. As shown in Fig. 2(a), an inclined surface in which an inner diameter of the sleeve 60 is reduced from a lower end surface is provided in a lower inner peripheral surface of the sleeve 60. Further, a taper seal portion 62a in which a gap size is expanded toward a lower side in a direction of a rotational axis is formed in a gap between the inclined surface of the sleeve 60 and an outer peripheral surface of the shaft 58 opposing to the inclined surface in radial direction. Further, as shown in Fig. 2(b), an inclined surface in which a diameter of an outer shape of the shaft 58 is reduced from an outer peripheral surface is provided in an approximately center portion of the outer peripheral surface of the shaft 58. Further, taper seal portions 62b and 62c in which gap sizes are expanded to-

ward an inner side in rotational axis direction are formed in a gap between the inclined surface of the shaft 58 and an inner peripheral surface of the sleeve 60 opposing to the inclined surface in radial direction. A lubricating oil is retained in the taper seal portions 62a, 62b and 62c, a surface tension of the lubricating oil and an ambient air pressure are balanced in the taper seal portions 62a, 62b and 62c, and interfaces 64a, 64b and 64c between the lubricating oil and the air are formed in a meniscus shape.

[0033] The interface of the lubricating oil is retained by the surface tension in macroscopic phenomenon, however, the oil is diffused along the surfaces of the shaft 58 and the sleeve 60 in macroscopic phenomenon so as to tend to ooze the oil to an outer side of the hydrodynamic bearing 56. In order to prevent this phenomenon, oil repellent films 66 are formed on surfaces of the shaft and/or the sleeve near and/or adjacent to areas of the interfaces 64a, 64b and 64c of the lubricating oil. Since the oil repellent films 66 are provided on the surfaces thereof with a nature of keeping a molecule of the lubricating oil surface off, it is possible to prevent the lubricating oil from oozing and leaking out of the bearing.

[0034] Each lubricating oil film 66 is formed by applying an oil

repellent solution to the predetermined area on the surfaces of the shaft 58 and/or the sleeve 60, and thereafter removing a solvent by means of an oven heating or the like.

[0035] The oil repellent solution is obtained by dissolving an oil repellent to the solvent. It is preferable that a polytetrafluoroethylene (PTFE), a polyfluorovinylidene (PVDF), a polyfluorovinyl (PVF), an ethylene-tetrafluoroethylene copolymer (ETFE), an ethylene-chlorotrifluoroethylene copolymer (ECTFE), or a fluorocarbon resin such as a resin in which a part of molecular structure thereof is substituted by a functional group is employed as the oil repellent. In particular, a perfluoro resin is preferable in view of low surface energy and a high oil repellent performance. In the case that the fluorocarbon resin is employed as the oil repellent, it is preferable that the medium used as the solvent employs a fluorine compound group medium. The medium used as the solvent generally has a volatile property.

[0036] Next, a description will be given of an apparatus for supplying the oil repellent solution. The apparatus in Fig. 3 is provided with a holding device 12 for a part such as a shaft onto which the oil repellent solution is applied, a

pair of oil repellent solution supplying nozzles 14, a suction apparatus 16 for executing a depressurizing suction for peeling and sucking an excess oil repellent solution in the oil repellent solution applied to the part, and a pair of solvent supplying pipes 18 for supplying the solvent of the oil repellent.

[0037] The description given below as an example that the oil repellent solution is applied to the shaft of the hydrodynamic bearing. In this case, for convenience of description, positional relationships between the positions of parts of the coating apparatus are described in rotational axis direction of the shaft. The part holding device 12 holds a lower end portion or an upper end portion of the shaft 58 corresponding to the oil repellent solution coated part, is driven by a rotation driving apparatus (not shown), and rotates the holding shaft 58 in one direction. In this example, the part holding device 12 drives the part in a counterclockwise direction as shown in Fig. 3. In this case, a clockwise direction may be set by taking an amount of application of the oil repellent solution and a solidifying time into consideration. The oil repellent solution is applied to two areas apart from each other at a fixed distance in the direction of the rotational axis, on the outer

peripheral surface of the shaft 58. In this case, the area to which the oil repellent solution is applied is not limited to two areas, and may be set to one area or three areas. Further, the area in the shaft 58 to which the oil repellent solution is applied is not limited to the outer peripheral surface of the shaft 58, but may be the upper end surface or the lower end surface of the shaft 58. Further, it is not always necessary to rotate the shaft 58, however, in the case of not rotating, it is necessary that the oil repellent solution supplying area and the coated area on the part are relatively displaced by the other means.

[0038] A pair of oil repellent solution supplying nozzles 14 are driven vertically, and leading end portions of the respective supplying nozzles 14 are arranged just above a part of a predetermined area around the outer peripheral surface of the shaft 58 held by the part holding device 12 respectively at a slight gap. Each of the supplying nozzles 14 applies the oil repellent solution delivered from a delivery apparatus (not shown) onto the part of the predetermined area on the outer peripheral surface of the shaft 58 in this state. In this case, it is preferable that the supplying nozzle 14 applies the oil repellent solution onto the part of the predetermined area on the outer peripheral

surface of the shaft 58 from an upper side. This is because of applying the oil repellent solution discharged from the supplying nozzle 14 accurately to the part of the predetermined area of the shaft 58 on the basis of an operation of the gravity. However, the structure is not limited to this.

[0039] The oil repellent solution applied onto the shaft 58 mentioned above is generally applied more than a proper amount. Accordingly, if the excess oil repellent solution is left untouched, the applied oil repellent solution diffuses over the predetermined area on the shaft 58 caused by a diffusion and a flow of the solution. In order to prevent this matter, a suction apparatus 16 shown in Fig. 3 is used for sucking the excess oil repellent solution more than the suitable amount. The suction apparatus 16 has a pair of approximately rectangular protruding portions 16b on an upper surface of a pedestal 16a, and each of the protruding portions 16b has a recess portion 16c which has a curved surface, a part of a cylindrical surface having a slightly larger diameter than an outer diameter of the shaft 58 corresponding to the part to be coated, open in an upper side, as shown in Fig. 3.

[0040] A suction port 16d is formed in a center portion with re-

spect to a width in rotational axis direction, on the curved surface of each of the recess portions 16c. In an opening portion 16e (refer to Fig. 9) of the suction port 16d, a width in rotational axis direction of the opening portion 16e is approximately equal to a width in rotational axis direction of the predetermined area of the outer peripheral surface of the shaft 58 to which the oil repellent solution is applied. Further, the opening portion 16e is formed on the recess portion 16c at a center area of the width in rotational axis direction of the rectangular protruding portion 16b. As shown in Fig. 9, the suction port 16d has a depth from the opening 16e to the lower side (that is down ward side, the direction toward a suction tube 16f as shown in Fig. 9), and a down ward side of the suction port 16d is inclined in an approximately funnel shape from the opening 16e to a bottom portion in down ward, that is a center portion. Further, an upper end of the suction tube 16f extending to a lower side is open to the center portion. The suction tube 16f is communicated with an exhaust apparatus such as an exhaust pump (not shown) or the like.

[0041] The oil repellent solution coated on the shaft 58, and the excess oil repellent solution is sucked by the suction port

16d mentioned above, and the excess oil repellent solution is recovered along the suction tube 16f. However, the oil repellent solution having the volatile is solidified on the suction port 16d for a short time, and closes the suction tube 16f if it is left untouched. In order to dissolve the solidified oil repellent solution and smoothly recover the oil repellent solution, a solvent supplying pipe 18 is connected to an inner side of the suction port 16d (Figs. 3 to 9). Further, an opening portion 18a of the solvent supply tube 18 is open to a position for supplying the solvent to the suction port 16d. The solvent is supplied to the opening portion 18a in the solvent supplying pipe 18 from a solvent supplying apparatus (not shown) through the solvent supplying pipe 18. Any solvent may be employed as far as the solvent dissolves the oil repellent, however, the same solvent as the solvent used in the oil repellent solution is preferable.

[0042] In this case, it is preferable to supply the solvent from an upstream side (a left side in Fig. 9) in the rotational direction of the shaft 58 in the suction port 16d. In other words, it is preferable to arrange the opening portion 18a of the solvent supply tube 18 in an upstream side in the rotational direction of the shaft 58 in the suction port

16d. This is because the oil repellent solution coated in the upper portion of the predetermined area of the shaft 58 to which the oil repellent solution is applied flows more in the upstream side than in the downstream side in the rotation. Accordingly, it is possible to securely prevent the solid-state oil repellent from being generated from the sucked oil repellent solution, by supplying the solvent to the upstream side in the rotational direction of the shaft 58. Further, the solvent supply tube 18 is not limited to this, and may be provided, for example, in both the upstream side and the downstream side.

[0043] Next, a description will be given of a first embodiment for applying the oil repellent solution with reference to Figs. 3 to 8.

[0044] First, as shown in Fig. 3, the shaft 58 is horizontally held by the part holding device 12, and the part holding device 12 is rotated in the counterclockwise direction in Fig. 3 (a displacing step). The pedestal 16a is positioned in the lower side of the shaft 58, and the oil repellent solution supplying nozzle 14 is positioned in the upper side of the shaft 58.

[0045] Next, as shown in Fig. 4, the pedestal 16a is moved upward, and the recess portion 16c in each of the protruding

portions 16d of the pedestal 16a is arranged in parallel just below the center axis of the shaft 58 held by the part holding device 12. At this time, a predetermined radial gap (for example, 0.5 to 4 mm, preferably 1 to 2 mm) is formed between the recess portion 16c and the outer peripheral surface of the shaft 58. Further, the opening portion 16e of the recess portion 16c is opposed to a part of the predetermined area on the outer peripheral surface of the shaft 58 onto which the oil repellent solution should be applied, in radial direction. In this case, it is preferable that the radial gap between the recess portion 16c and the outer peripheral surface of the shaft 58 is approximately constant in the axial direction except the opening portion 16e. Further, the suction apparatus 16 is operated at the same time of moving upward the pedestal 16a, and the suction is started.

[0046] Further, as shown in Fig. 5, a pair of oil repellent solution supplying nozzles 14 are moved downward, and the leading end portions of the oil repellent solution supplying nozzles 14 are arranged just above the part of the predetermined area of the outer peripheral surface of the shaft 58 respectively at the slight gap. The opening portion 16e of the suction port 16d is positioned just below the lead-

ing end portions of the oil repellent solution supplying nozzles 14 and the part of the predetermined area of the outer peripheral surface of the shaft 58.

[0047] Subsequently, as shown in Fig. 6, the application of the oil repellent solution supplied through the oil repellent solution nozzles 14 is started with respect to the parts of the predetermined two areas apart from each other in the axial direction on the outer peripheral surface of the rotating shaft 58 (a supplying step). Since the oil repellent solution is applied to the part of the predetermined area while rotating the shaft 58, it is possible to apply the oil repellent solution all around the periphery of each of the predetermined areas on the outer peripheral surface of the shaft 58. At the same time (or prior to this), the solvent supply into the suction port 16d from the opening portion 18a of the solvent supply tube 18 is started (a solvent supplying step).

[0048] At this time, as mentioned above, the predetermined radial gap is formed between the recess portion 16c and the outer peripheral surface of the shaft 58. Accordingly, the suction force generated by the intake air current flowing from both sides in the axial direction of the shaft 58 through the portion between the recess portion 16c and

the outer peripheral surface of the shaft 58 and exhausted from the opening portion 16e of the suction port 16d is applied to the oil repellent solution applied to the part of the predetermined area on the outer peripheral surface of the shaft 58 and flowing downstream, by operating the suction apparatus 16. Accordingly, it is possible to control the spread of the oil repellent solution in the predetermined area on the outer peripheral surface of the shaft 58, and the applied excess oil repellent solution is sucked and removed (a peeling step).

[0049] Further, since an evaporation of the solvent in the applied oil repellent solution is promoted by the sucked air current, it is possible to precisely control the area in which the oil repellent solution circulates around on the outer peripheral surface of the shaft 58 and the oil repellent film is formed, in the axial direction. Further, it is possible to more improve a uniformity of the thickness of the oil repellent solution applied to the predetermined area on the outer peripheral surface of the shaft 58.

[0050] Further, the oil repellent solution supplying nozzles 14 are not in contact with the outer peripheral surface of the shaft 58. Accordingly, it is possible to prevent the dusts or the like from being generated, due to the contact of the

oil repellent solution supplying nozzles 14 with the outer peripheral surface of the shaft 58. Further, the suction apparatus 16 is not in contact with any of the oil repellent solution applied to the predetermined area on the outer peripheral surface of the shaft 58 and the predetermined area. Accordingly, it is possible to prevent the film thickness of the oil repellent film formed after the application from being uneven, due to the contact of the suction apparatus 16 with the oil repellent solution applied to the predetermined area on the outer peripheral surface of the shaft 58, and it is possible to prevent the dusts or the like from mixing in the oil repellent film, due to the contact.

[0051] Further, since the evaporation of the solvent is promoted in the oil repellent solution applied to the predetermined area on the outer peripheral surface of the shaft 58, due to the suction air current, the solid-state oil repellent tends to be generated together with the evaporation of the solvent. In the case that the volatile solvent is employed as the solvent for the oil repellent solution, the solid-state oil repellent tends to be generated particularly. However, in the present embodiment, the solvent is further added to the oil repellent solution by sucking the solvent by means of the suction apparatus 16 while supply-

ing the solvent dissolving the oil repellent into the suction port 16d (a recovering step). Accordingly, it is possible to prevent the solid-state oil repellent from being generated from the sucked oil repellent solution. Therefore, it is possible to prevent the suction force of the suction apparatus 16 from being lowered, and it is possible to prevent a suction inability, due to the generation of the solid-state oil repellent.

[0052] Finally, as shown in Fig. 5, when the application of the oil repellent solution to the predetermined area on the outer peripheral surface of the shaft 58 is finished, the oil repellent solution supplying nozzles 14 are moved upward, and is moved apart from the shaft 58. At this time, the solvent supplying apparatus continuously supplies the solvent into the suction port 16d from the opening portion 18a, and the suction apparatus 16 continuously sucks.

[0053] As shown in Fig. 6, after the suction by the suction apparatus 16 is sufficiently executed, the suction is stopped, and the solvent supply from the solvent supplying apparatus is stopped as well as the pedestal 16a is moved downward. Further, the rotation of the shaft 58 is stopped.

[0054] Next, a description will be given of a second embodiment for applying the oil repellent solution with reference to Fig. 10. In the present embodiment, a description will be given of a method of applying the oil repellent solution to a sleeve 60.

[0055] As shown in Fig. 10, the sleeve 60 is held by a rotating part holding device 72. An oil repellent solution supplying nozzle 74 applies the oil repellent solution to the sleeve 60 by an oil repellent solution supply apparatus (not shown) at a time of operating. An oil repellent solution suction nozzle 76 sucks the oil repellent solution applied by a suction apparatus (not shown) at a time of operating.

[0056] First, the sleeve 60 is horizontally held by the holding device 72. Next, leading end portions of the oil repellent solution supplying nozzle 74 and the oil repellent solution suction nozzle 76 are arranged at positions slightly apart from each other just above a predetermined area on an inner peripheral surface of the sleeve 60.

[0057] Subsequently, the oil repellent solution suction nozzle 76 is operated and the suction is started. At the same time of operating the oil repellent solution suction nozzle 76, or after the operation, the oil repellent solution supplying nozzle 74 is operated, and the oil repellent solution is ap-

plied to the part of the predetermined area of the sleeve 60. Further, when the oil repellent solution supplying nozzle 74 finishes applying to the predetermined area of the sleeve 74, the oil repellent solution supplying nozzle 74 is moved upward, and is moved apart from the sleeve 74. At this time, the oil repellent solution suction nozzle 76 continuously sucks.

[0058] Finally, after the suction is sufficiently executed by the oil repellent solution sucking nozzle 76, the suction is stopped, and the oil repellent solution suction nozzle 76 is moved upward and is moved apart from the sleeve 60. Further, the rotation of the part holding device 72 is stopped.

[0059] In accordance with the present embodiment, the same operation and effect as those of the first embodiment can be obtained by using the method of applying the oil repellent solution and the method of forming the oil repellent film.

[0060] Next, a description will be given of an embodiment for cleaning the oil repellent solution supplying nozzles 14 and 74, with reference to Figs. 11 to 14.

[0061] There is a case that the oil repellent solution supplying nozzles 14 and 74 can not discharge the oil repellent so-

lution due to the solidification of the oil repellent, or a case that the discharge amount is small.

[0062] In the case mentioned above, first, as shown in Fig. 11, it is checked in the other places before applying the oil repellent solution to the shaft 58 and the sleeve 60 whether or not the oil repellent solution is discharged from the leading end portions of the oil repellent solution supplying nozzles 14 and 74 (a checking step).

[0063] As shown in Fig. 12, a solvent container 22 reserving a solvent 20 dissolving the oil repellent is positioned in a lower side of the leading end portions of the oil repellent solution supplying nozzles 14 and 74. Further, as shown in Fig. 13, the oil repellent solution supplying nozzles 14 and 74 are moved downward, and the discharging operation is executed in a state in which the leading end portions are positioned within the solvent 20 (a step of dipping the leading end portions of the oil repellent solution supplying nozzles).

[0064] Next, as shown in Fig. 14, the oil repellent solution supplying nozzles 14 and 74 are moved upward so as to be pulled up from the solvent 20, the solvent container 22 is returned to the original position, and thereafter, the discharge test is again executed.

[0065] If a good discharge by the oil repellent solution supplying nozzles 14 and 74 is confirmed, the step goes to the oil repellent solution applying work. Unless it is confirmed, the steps in Figs. 12 to 14 are repeated(a clogging canceling step).

[0066] Since it is possible to apply the oil repellent solution to the predetermined area of the shaft 58 and the sleeve 60 at a high reliability on the basis of the steps mentioned above, the quality of the oil repellent film in accordance with a mass production is stable.

[0067] The description is given above of each of the embodiments of the spindle motor manufacturing method in accordance with the present invention, however, the present invention is not limited to each of the embodiments mentioned above, and can be variously modified and changed within the scope of the invention.

[0068] For example, the spindle motor in accordance with the present invention is of the shaft fixed type, however, the present invention can be applied to a shaft rotation type spindle motor.

[0069] Further, the oil repellent film can be formed on the outer peripheral surface of the shaft of the spindle motor in accordance with the present invention, by employing the

apparatus in accordance with the second embodiment.

[0070] Further, the step of peeling a part of the oil repellent solution is not limited to the method of sucking the oil repellent solution supplied to the predetermined area. For example, a method of blowing away the oil repellent solution may be employed.